

SPECIFICATION SHEET

POLISHED PLASTER SELECTOR **RANGE - SMOOTH**



A luxurious finish with a natural stone look for interior use.

Smooth is natural, mid-sheen finish with visible crushed marble and light burnishing from the trowel application. The Smooth polished plaster finish is similar to the marmorino stucco, used extensively in northern Italy during the Renaissance period as an internal and external wall finish and as a background for the ornate frescoes which dominated much of the decoration of that time.







ZERO VOC



RATED





SPECIFICATIONS

POLISHED PLASTER SELECTOR RANGE - SMOOTH

DESCRIPTION:	Armourcoat Smooth Polished Plaster Selector Range
MANUFACTURER:	Armourcoat Ltd
CONTACT DETAILS:	Address: Morewood Close, Sevenoaks, Kent, United Kingdom, TN13 2HU Telephone: +44 (0)1732 460668 Web: www.armourcoat.com Email: specsales@armourcoat.co.uk
COMPONENTS:	Natural lime and marble
REACTION TO FIRE:	EN 13501-1:2018: A2-s1,d0
FIRE RATING:	ASTM E84: Flame Spread index: 10, Smoke Development Index: 10, Classification: 1
VOC CONTENT AND EMISSIONS:	BBREEAM International v2.0 (2016): Exemplary Level, French VOC Label: A+, Indoor Air Comfort: Pass, ABG/AgBB: Pass, Belgian Regulation: Pass, ASTM D2369: <1, SCAQMD Rule 1113: Pass, LEED v4 + v4.1 BETA: Pass
PREPARATORY REINFORCING SKIMCOAT:	Armourcoat Anticrack OR not required
	Armourcoat Anticrack OR not required As drawing
REINFORCING SKIMCOAT:	
REINFORCING SKIMCOAT: LOCATION:	As drawing
REINFORCING SKIMCOAT: LOCATION: HARDNESS: RECYCLED CONTENT	As drawing Shore D Hardness test: 64, ASTM D3363 Pencil Harness: 5H+
REINFORCING SKIMCOAT: LOCATION: HARDNESS: RECYCLED CONTENT (MINIMUM):	As drawing Shore D Hardness test: 64, ASTM D3363 Pencil Harness: 5H+ 29%
REINFORCING SKIMCOAT: LOCATION: HARDNESS: RECYCLED CONTENT (MINIMUM): SYSTEM WEIGHT:	As drawing Shore D Hardness test: 64, ASTM D3363 Pencil Harness: 5H+ 29% 2.40-3.0 kg/m²
REINFORCING SKIMCOAT: LOCATION: HARDNESS: RECYCLED CONTENT (MINIMUM): SYSTEM WEIGHT: EMBODIED CARBON: TECHNICAL CHARACTERISTICS,	As drawing Shore D Hardness test: 64, ASTM D3363 Pencil Harness: 5H+ 29% $2.403.0 \text{ kg/m}^2$ $\text{EN15804 +A2: } 0.34 \text{ Kg CO}_2\text{e}$
REINFORCING SKIMCOAT: LOCATION: HARDNESS: RECYCLED CONTENT (MINIMUM): SYSTEM WEIGHT: EMBODIED CARBON: TECHNICAL CHARACTERISTICS, OTHER:	As drawing Shore D Hardness test: 64, ASTM D3363 Pencil Harness: 5H+ 29% 2.40-3.0 kg/m² EN15804 +A2: 0.34 Kg CO ₂ e Mould and mildew resistance, to ASTM D3274: 10/10/10