

SPECIFICATION SHEET

## POLISHED PLASTER SELECTOR RANGE - LEATHERSTONE



## A modern re-imagination of a classic surface finish for internal use.

Leatherstone is a natural lime and marble polished plaster that combines the look of lightly polished stone with the surface interest of aged leather. It has an open, non-directional texture with distinctive surface movement that can be further enhanced with use of a tinted, metallic or pearlescent sealer.







SUSTAINABLE ACCREDITATIONS ZERO VOC

FIRE RATED





## SPECIFICATIONS

## POLISHED PLASTER SELECTOR RANGE - LEATHERSTONE

| DESCRIPTION:                            | Armourcoat Leatherstone Polished Plaster Selector Range  |
|---|--|
| MANUFACTURER:                           | Armourcoat Ltd   |
| CONTACT DETAILS:                        | Address: Morewood Close, Sevenoaks, Kent, United Kingdom, TN13 2HU<br>Telephone: +44 (0)1732 460668<br>Web: www.armourcoat.com<br>Email: specsales@armourcoat.co.uk  |
| COMPONENTS:                             | Natural lime and marble  |
| REACTION TO FIRE:                       | EN 13501-1:2018: A2-s1,d0  |
| FIRE RATING:                            | ASTM E84: Flame Spread index: 10, Smoke Development Index: 10,<br>Classification: 1  |
| VOC CONTENT<br>AND EMISSIONS:           | BREEAM International v2.0 (2016): Exemplary Level, French VOC Label:<br>A+, Indoor Air Comfort: Pass, Indoor Air Comfort Gold: Pass, ABG/AgBB:<br>Pass, Belgian Regulation: Pass, ASTM D2369: <1, SCAQMD Rule 1113:<br>Pass, LEED v4 + v4.1 BETA: Pass |
| PREPARATORY<br>REINFORCING SKIMCOAT:    | Armourcoat Anticrack OR not required   |
| LOCATION:                               | As drawing   |
| HARDNESS:                               | Shore D Hardness test: 64, ASTM D3363 Pencil Harness: 5H+  |
| RECYCLED CONTENT<br>(MINIMUM):          | 44%  |
| SYSTEM WEIGHT:                          | 3.30-3.90 kg/m²  |
| EMBODIED CARBON:                        | EN15804 +A2: 0.34 Kg CO <sub>2</sub> e   |
| TECHNICAL<br>CHARACTERISTICS,<br>OTHER: | Mould and mildew resistance, to ASTM D3274: 10/10/10   |
| COLOUR:                                 | Insert colour selection  |
| SEALER:                                 | Aquawax as standard  |