

Armourcoat Limited  
Unit 2-3a, Morewood Close  
London Road  
TN13 2HU Sevenoaks  
UNITED KINGDOM

Eurofins Product Testing A/S  
Smedeskovvej 38  
8464 Galten  
Denmark

CustomerSupport@eurofins.com  
www.eurofins.com/VOC-testing

## TEST REPORT

### VOC Content

13 January 2022

#### 1 Sample Information

Sample name	P80/P70 Spatulata
Sample no.	392-2021-00619409
Stated production date	16/11/2021
Batch No.	21093
Sample reception	09/12/2021

#### 2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
SCAQMD Rule 1113	Pass	February 2016
LEED v4.1 (VOC Content)	Pass	February 2021

Full details based on the testing and direct comparison with limit values are available in the following pages  
Regarding pass/fail decision rule please see appendix



Pernille Krintel  
Analytical Service Manager



Janne Rothmann Norup  
Analytical Service Manager

### 3 Applied Test Methods

#### 3.1 General Test References

Regulation, protocol or standard	Scope	Version
SCAQMD Rule 1113	Architectural coatings	February 2016

#### 3.2 Specific Laboratory Sampling and Analyses

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection	Uncertainty U <sub>m</sub>
				[g/L]	%
Solids Content	ASTM D2369	2020	71 M 544830	1	10
VOC	ASTM D2369	2020	71 M 544830	1	10
Density *	Internal method	-	71 M 543130	-	10

#### 3.3 Preparation of the Test Specimen

The sample was homogenised and applied directly onto the test dish.

## 4 Results

#### 4.1 VOC content

	Remarks on the test results	Results	Unit
Density *	Tested by the lab	1.6	g/mL
Water Content <sup>1</sup>	Tested by the lab	32.1	% (w/w)
Exempt compounds *	Assumed to be 0	0	% (w/w)
Solids Content	Tested by the lab	79	% (w/w)
VOC content (less water)	Calculated based on the results above	< 1	g/L

#### 4.2 Comparison with Limit Values of VOC Content (less Water)

Parameter	Results	Product type	Regulation or protocol	VOC limit
	[g/L]			[g/L]
VOC content	< 1	Trowel Applied Coating	SCAQMD Rule 1113	50

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity.

## 5 Appendices

### 5.1 How to Understand the Results

#### 5.1.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- \* Not a part of our accreditation
- ± Please see section regarding uncertainty in the Appendices
- 1 Analysed by another Eurofins laboratory

### 5.2 Description of VOC Content Test

#### 5.2.1 Testing of VOC

Volatile content of the sample was determined gravimetrically by heating to 110 °C in 60 minutes. Multicomponent products are mixed according to the manufacturer's instructions and allowed to cure before heating.

The result is the average of two replicates. The result was calculated as:

$$VOC = \frac{([g \text{ All Volatiles}] - [g \text{ Water}] - [g \text{ Exempt Compounds}])}{([liter \text{ Material}] - [liter \text{ Water}] - [liter \text{ Exempt Compounds}])}$$

#### 5.2.2 Testing of Density

The density was calculated using gravimetric and volumetric determination. The result is the average of three determinations.

#### 5.2.3 Testing of Water Content

The water content was determined using a Karl-Fischer titration.

### 5.3 Uncertainty of the Test Method

Um(%): The expanded uncertainty Um is equal to 2 x RSD%.

### 5.4 Decision Rules

Eurofins Product Testing A/S, declare statement of conformity based on the "Binary Statement for Simple Acceptance Rule" described in ILAC's "Guidelines on decision Rules and Statements of Conformity" ILAC-G8:09/2019.

This means that results above the detection limit are always reported with two significant digits. Results are evaluated with the same number of significant digits as the corresponding limit values, and conformity is based on results being less than or equal to limit values.

For limit values with more than two significant digits, the third digit will be used to confirm whether a result is

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity.

below or equal to the limit value. It will always be indicated in the evaluation table if this expanded evaluation is performed.

For further information please visit [www.eurofins.dk/product-testing/om-os/beslutningsregler/](http://www.eurofins.dk/product-testing/om-os/beslutningsregler/)

## 5.5 Version History

Report date	Report number	Modification
13/01/2022	392-2021-00619409_XG_EN	Current version